

3M™ Fluorinert™ Electronic Liquid FC-770

Product description

3M™ Fluorinert™ Electronic Liquid FC-770 is a thermally stable, fully-fluorinated liquid that has ideal properties for use as a heat transfer fluid in a variety of industries.

The inertness of Fluorinert liquid FC-770 permits its use as a direct contact single- and two-phase coolant in certain supercomputers and sensitive military electronics. Its high dielectric strength and electrical resistivity are ideal for applications in high voltage transformers and power electronics.

In the semiconductor manufacturing industry, its wide liquid range makes Fluorinert liquid FC-770 suited for cooling ion implanters, dry etchers and CVD machines. Its low pour point also permits its use in thermal shock and test equipment.

Typical physical properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes. Final product specifications and testing methods will be outlined in the products Certificate of Analysis (COA) that is shipped with the commercialized product. All values @ 25°C unless otherwise specified.

Properties	3M™ Fluorinert™ Electronic Liquid FC-770
Appearance	Clear, colorless
Average Molecular Weight	399 (g/mol)
Boiling Point (@ 1 atm)	95 °C (203°F)
Pour Point	-127 °C (-196.6°F)
Calculated Critical Temperature	238 (°C)
Calculated Critical Pressure	2.47 x 10 ⁶ (pa)
Vapor Pressure	6.568 x 10 ³ (pa)
Latent Heat of Vaporization (at normal boiling point)	85.9 (J/g)
Liquid Density	1793 (kg/m ³)
Kinematic Viscosity	0.79 (cSt)
Absolute Viscosity	1.359 (cP)
Liquid Specific Heat	1038 (J kg ⁻¹ °C ⁻¹)
Liquid Thermal Conductivity	0.063 (W m ⁻¹ °C ⁻¹)
Coefficient of Expansion	0.00148 (°C ⁻¹)
Surface Tension	14.8 (dynes/cm)
Refractive Index	1.27
Ozone Depletion Potential	0
Flash Point	None

3M™ Fluorinert™ Electronic Liquid FC-770

Typical electrical properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes. Final product specifications and testing methods will be outlined in the products Certificate of Analysis (COA) that is shipped with the commercialized product. All values @ 25°C unless otherwise specified.

Properties	3M™ Fluorinert™ Electronic Liquid FC-770
Dielectric Strength (0.1" gap)	>40 (kV)
Dielectric Constant (@ 1 kHz)	1.9
Electrical Resistivity (ASTM D-257)	>3 x 10 ¹⁴ (ohm cm)

Heat transfer properties

The following formulas can be used to calculate the specific heat, density, viscosity and vapor pressure of 3M™ Fluorinert™ Electronic Liquid FC-770 at various temperatures.


Specific Heat (J kg⁻¹ °C⁻¹) = 997 + 1.615 (T, °C)

Thermal Conductivity (estimate) (W m⁻¹ °C⁻¹) = 0.065 – 0.00008 (T, °C)

Density (kg/m³) = 1860 – 2.66 (T, °C)

Vapor Pressure (mm Hg) = EXP [16.21 – 3028.88/(T, °C +221)]

The following graph can be used to determine the viscosity of Fluorinert liquid FC-770 over the indicated temperature range.



Materials compatibility

Fluorinert liquid FC-770 is compatible with most metals, plastics and elastomers. Contact 3M for more information.

3M™ Fluorinert™ Electronic Liquid FC-770

Storage and shelf life

The shelf life of 3M™ Fluorinert™ Electronic Liquid FC-770 is 36 months from the date of manufacture when stored in the original packaging materials and stored at 21°C (70°F) and 50% relative humidity.

Toxicity profile

Not for specification purposes.

3M™ Fluorinert™ Electronic Liquid FC-770 is virtually non-irritating to the eyes and skin. The product also demonstrates very low toxicity. It was not mutagenic in the Ames assay, and is non clastogenic. A Safety Data Sheet (SDS) is available from www.3m.com/SDS.

Safety and handling

Before using this product, please thoroughly read the current product SDS and label, following all applicable safety precautions described therein (e.g., recommended storage and safe handling, appropriate exposure controls and personal protective equipment (PPE), addressing accidental spills, disposal considerations, etc.). Fluorinert liquid FC-770 is nonflammable and is resistant to thermal breakdown and hydrolysis during typical use and storage.

Environmental properties

Fluorinert Electronic Liquid FC-770 has zero ozone depletion potential. Additionally, this product has negligible photochemical reactivity and therefore it does not appreciably contribute to ground-level smog formation. As such, it is not defined or regulated by the U.S. EPA as a volatile organic compound (VOC).

As a perfluorocarbon (PFC), this product has a high global warming potential and a long atmospheric lifetime. As such, its use should be carefully managed to minimize emissions.

3M recommends that users of Fluorinert Electronic Liquid FC-770 further limit emissions by employing good conservation practices, and by implementing recovery, recycling and/or proper disposal procedures. In general, 3M recommends that Fluorinert-branded liquids be disposed of by incineration at a permitted industrial waste facility capable of handling halogenated materials, in accordance with all applicable local, regional, national, and/or international regulations. See product SDS for further details. 3M also offers a Used Fluid Disposal Program.

www.parallax-tech.com>Back